

# COIL COLOR CHART



Final color selections should be made from metal color chips.

Gauge and finish options vary by panel profile. For the most current information available, as well as details about paint warranty coverage, visit our website: [muellerinc.com](http://muellerinc.com).

All Signature® 200 and 300 colors are Cool Roof compliant through the CRRC-1 Program. Visit [coolroofs.org](http://coolroofs.org) for more details.


















## SIGNATURE® 200

Silicone Modified Polyester (SMP)

				
Polar White (Polyester)	High Gloss White	White	Bright White	Hawaiian Blue
				
Cobalt Blue	Light Stone	Saddle Tan	Desert Sand	Coffee Brown
				
Burnished Slate	Ash Gray	Deep Gray	Charcoal Gray	Evergreen
				
Ivy Green	Scarlet Red	Rustic Red	Wine Red	True Black
				
Matte Black	Smokey Pewter	Dark Charcoal	Dark Bronze	Orange (Polyester)

## SIGNATURE® 300

Polyvinylidene Fluoride (PVDF) | Low Gloss

				
Snow White	Bone White	Pacific Blue	Harbor Blue	Almond
				
Brownstone	Medium Bronze	Midnight Bronze	Tundra	Slate Gray
				
Storm Gray	Classic Green	Brite Red	Colonial Red	Midnight Black
				
Copper Metallic*	Silver Metallic*			

\*Metallic colors incur an upcharge, panels and trim are directional and must be installed in the same direction to prevent perceived shade variances.

# COLORS AVAILABLE BY COIL TYPE

SIGNATURE® 200 24 Gauge SMP Colors		26 Gauge Tensile Strength 50/80 ksi	24 Gauge Tensile Strength 50 ksi	22 Gauge Tensile Strength 50 ksi	Thermal Emittance <sup>1</sup> Range 0 to 1 (±0.02)	Solar Reflectance <sup>2</sup> (Initial SR) Range 0 to 1	Film Integrity (Years)	Color Fade ASTM D 2244 (Years)	Chalk ASTM D 4214, Method A (Years)
Galvalume® Plus	●	●	●	●	0.19	0.69	n/a	n/a	n/a
Polar White (Polyester)	●				0.88	0.61	25	n/a	n/a
High Gloss White	●				0.86	0.73	45	30	30
White	●				0.83	0.62	45	30	30
Bright White	●	●	●	●	0.88	0.70	45	30	30
Hawaiian Blue	●	●	●		0.86	0.32	45	30	30
Cobalt Blue	●	●	●		0.83	0.26	45	30	30
Light Stone	●	●	●		0.87	0.56	45	30	30
Saddle Tan	●	●	●		0.87	0.47	45	30	30
Desert Sand	●	●	●		0.88	0.43	45	30	30
Coffee Brown	●	●	●		0.86	0.29	45	30	30
Burnished Slate	●	●	●		0.86	0.33	45	30	30
Ash Gray	●	●	●		0.87	0.46	45	30	30
Deep Gray	●	●	●		0.86	0.32	45	30	30
Charcoal Gray	●	●	●		0.86	0.36	45	30	30
Evergreen	●	●	●		0.83	0.30	45	30	30
Ivy Green	●	●	●		0.87	0.29	45	30	30
Scarlet Red	●	●	●		0.86	0.31	45	30	30
Rustic Red	●	●	●		0.87	0.38	45	30	30
Wine Red	●	●	●		0.83	0.29	45	30	30
True Black	●	●	●		0.83	0.31	45	30	30
Matte Black	●	●	●		0.88	0.26	45	30	30
Smokey Pewter	●	●	●		0.88	0.38	45	30	30
Dark Charcoal	●	●	●		0.88	0.19	45	30	30
Dark Bronze	●	●	●		0.87	0.23	45	30	30
Orange* (Polyester)	●	●	●		n/a	n/a	n/a	n/a	n/a
Weathered Steel*				●	n/a	n/a	n/a	n/a	n/a
SIGNATURE® 300 24 Gauge PVDF Colors		26 Gauge Tensile Strength 50/80 ksi	24 Gauge Tensile Strength 50 ksi	22 Gauge Tensile Strength 50 ksi	Thermal Emittance <sup>1</sup> Range 0 to 1 (±0.02)	Solar Reflectance <sup>2</sup> (Initial SR) Range 0 to 1	Film Integrity (Years)	Color Fade ASTM D 2244 (Years)	Chalk ASTM D 4214, Method A (Years)
Snow White			●		0.87	0.65	45	35	35
Bone White	●		●		0.86	0.68	45	35	35
Pacific Blue	●		●		0.83	0.25	45	35	35
Harbor Blue			●		0.86	0.27	45	35	35
Almond	●		●		0.88	0.64	45	35	35
Brownstone	●		●		0.88	0.47	45	35	35
Medium Bronze			●		0.86	0.34	45	35	35
Midnight Bronze			●		0.83	0.29	45	35	35
Tundra			●		0.83	0.35	45	35	35
Slate Gray			●		0.86	0.36	45	35	35
Storm Gray			●		0.86	0.30	45	35	35
Classic Green			●		0.88	0.27	45	35	35
Brite Red	●		●		0.83	0.25	45	35	35
Colonial Red			●		0.87	0.34	45	35	35
Midnight Black	●		●		0.83	0.25	45	35	35
Copper Metallic	●		●		0.75	0.35	45	35	35
Silver Metallic			●		0.75	0.35	45	35	35

<sup>1</sup> ASTM C 1371 Standard Test Method for Determination of Emittance of Materials Near Room Temperature Using Portable Emisimeters.

<sup>2</sup> ASTM C 1549 Standard Test Method for Determination of Solar Reflectance Near Ambient Temperature Using Portable Solar Reflectometer.

\*No warranty available for Orange or Weathered Steel.

Mueller, Inc. reserves the right to add or discontinue colors without notice.



CALL: 877-2-MUELLER (877-268-3553)  
 CLICK: MUELLERINC.COM  
 COME BY: OUR CONVENIENT LOCATIONS