

COIL COLOR AVAILABILITY

Color	29 Gauge Tensile Strength 80 ksi	26 Gauge Tensile Strength 80 ksi	24 Gauge Tensile Strength 50 ksi	22 Gauge Tensile Strength 50 ksi	Thermal Emittance ¹ Range 0 to 1	Solar Reflectance (TSR) ² Range 0 to 1	Film Integrity (Years)	Color Fade ASTM D 2244 (Years)	Chalk ASTM D 4214, Method A (Years)
Black		●	●		0.87 ± 0.02	0.25	40	30	30
Bright Copper		●	●		0.89 ± 0.02	0.42	35	35	35
Bright White™		●	●		0.89 ± 0.02	0.82	40	30	30
Burgundy		●			0.89 ± 0.02	0.16	40	30	30
Burnished Slate	●	●	●		0.89 ± 0.02	0.26	40	30	30
Charcoal	●	●	●		0.89 ± 0.02	0.33	40	30	30
Chestnut Brown		●			0.89 ± 0.02	0.29	40	30	30
Coco Brown	●	●	●		0.89 ± 0.02	0.31	40	30	30
Colony Green		●	●		0.89 ± 0.02	0.38	40	30	30
Deep Blue		●	●		0.89 ± 0.02	0.27	40	30	30
Deep Green		●	●		0.89 ± 0.02	0.25	40	30	30
Deep River Blue		●			0.89 ± 0.02	0.26	40	30	30
Desert Tan		●	●		0.87 ± 0.02	0.44	40	30	30
Forest Green		●			0.89 ± 0.02	0.25	40	30	30
Galvalume Plus	●	●	●	●	0.31 ± 0.02	0.68	20	20	20
Gold		●			0.89 ± 0.02	0.49	40	30	30
Hawaiian Blue	●	●			0.87 ± 0.02	0.31	40	30	30
High Gloss White	●				0.83 ± 0.02	0.67	40	30	30
Ivy Green	●	●	●		0.89 ± 0.02	0.31	40	30	30
Light Gray	●	●	●		0.87 ± 0.02	0.48	40	30	30
Light Stone	●	●	●		0.83 ± 0.02	0.59	40	30	30
Mansard Brown		●	●		0.89 ± 0.02	0.25	40	30	30
Marine Green		●			0.89 ± 0.02	0.39	40	30	30
Orange ³		●	●		0.47 ± 0.02	0.52	n/a	n/a	n/a
Patriot Red		●	●		0.80 ± 0.02	0.42	40	30	30
Rustic Brown		●			0.89 ± 0.02	0.31	40	30	30
Rustic Red	●	●	●		0.86 ± 0.02	0.36	40	30	30
Saddle Leather Brown		●	●		0.89 ± 0.02	0.30	40	30	30
Silver Metallic		●	●		0.83 ± 0.02	0.57	35	35	35
Smokestack Gray		●			0.88 ± 0.02	0.31	40	30	30
Smokey Pewter		●	●		0.84 ± 0.02	0.45	40	30	30
Sunset Red		●			0.89 ± 0.02	0.39	40	30	30
Tan	●	●	●		0.84 ± 0.02	0.50	40	30	30
Twilight Gray		●			0.84 ± 0.02	0.59	40	30	30
White	●	●	●	●	0.89 ± 0.02	0.59	40	30	30
A606 Weathering Steel				●	n/a	n/a	n/a	n/a	n/a

¹ASTM C 1371 "Standard Test Method for Determination of Emittance of Materials Near Room Temperature Using Portable Emissometers"

²ASTM C 1549 "Standard Test Method for Determination of Solar Reflectance Near Ambient Temperature Using a Portable Solar Reflectometer"

³No Warranty Available for Orange